

# RELIABILITY MONITOR

PRODUCT	MONITOR DATE	DATE CODE	ASSEMBLY FACILITY	ASSEMBLY LOT NO	PROCESS TYPE	PACKAGE TYPE
DS12885	Dec-95	9501 A2	ANAM, K.	DN444456AAG	1.2μ OX/NI	28 PLCC

## STRESS/JOB NO.

## READPOINT (Sample Size/No. of Fails)

Preconditioning (P/C):  
HTC Vapor Phase  
P-16742

Electrical  
231/0      Cum %  
0.0%

Sonoscan  
P-16771

Post Vapor Phase  
2/0

Infant / High Voltage Life  
125°C, 7.0 V.  
P-16772, P-16785

<u>48 Hr</u>	<u>336 Hr</u>	<u>1KHr</u>	<u>*Failure Rate</u>
231/0	77/1	76/0	67 Fits
	F1		

\*Chi Squared Method, 60% C. L., 55°C & 5.5V; Temperature Derating: Ea = 0.7 ev; Voltage Derating B = 1.0

Temp Cycle  
-55°C to +125°C  
P-16786

<u>300 ~</u>	<u>1K ~</u>	<u>Cum %</u>
39/0	39/0	0.0%

Biased Moisture  
85°C/85% RH, 5.5 V.  
P-16787

<u>274 Hr</u>	<u>959 Hr</u>	<u>Cum %</u>
77/0	77/0	0.0%

Autoclave  
121°C/100% RH, 2 Atmos  
P-16788

<u>96 Hr</u>	<u>Cum %</u>
38/0	0.0%

## Failure Mode

F1: Continuity