

# RELIABILITY MONITOR

PRODUCT	MONITOR DATE	DATE CODE	ASSEMBLY FACILITY	ASSEMBLY LOT NO	PROCESS TYPE	PACKAGE TYPE
DS2401	Dec-95	9544 B1	CARSEM	DM525683AH	1.2μ OX/NI	03 TO-92

**STRESS/JOB NO.**

**READPOINT  
(Sample Size/No. of Fails)**

Infant / High voltage Life 125°C, 7.0 V. P-16740, P-16792	<u>48 Hr</u> 228/3 F1	<u>336 Hr</u> 77/0	<u>1KHr</u> 77/0	<u>*Failure Rate</u> 137 Fits
---	-----------------------------	-----------------------	---------------------	----------------------------------

\*Chi Squared Method, 60% C. L., 55°C & 5.5V; Temperature Derating: Ea = 0.7 ev; Voltage Derating B = 1.0

Temp Cycle -55°C to +125°C P-16793	<u>300 ~</u> 36/0	<u>1K ~</u> 36/0	<u>Cum %</u> 0.0%
--	----------------------	---------------------	----------------------

Biased Moisture (HAST) 120°C/85% RH, 5.5 V. P-16794	<u>100 Hr</u> 77/0	<u>Cum %</u> 0.0%
---	-----------------------	----------------------

Autoclave 121°C/100% RH, 2 Atmos P-16795	<u>96 Hr</u> 38/0	<u>Cum %</u> 0.0%
--	----------------------	----------------------

**Failure Mode**

F1: 3-DQ Resistance