

# RELIABILITY MONITOR

PRODUCT	MONITOR DATE	DATE CODE	ASSEMBLY FACILITY	ASSEMBLY LOT NO	PROCESS TYPE	PACKAGE TYPE
DS5002	Jul-97	9722 M3	ANAM, K.	DN703157AAB	1.2μ OX/NI	80 PQFP

**STRESS/JOB NO.**

**READPOINT  
(Sample Size/No. of Fails)**

Preconditioning (P/C):  
HTC Vapor Phase  
P-20073

<u>Electrical</u>	<u>Cum %</u>
235/0	0.0%

Sonoscan  
P-20095

<u>Post Vapor Phase</u>
4/0

Infant / High Voltage Life  
125°C, 7.0 V.  
P-20096, P-20155

<u>48 Hr</u>	<u>336 Hr</u>	<u>1KHr</u>	<u>*Failure Rate</u>
231/0	77/0	77/0	30 Fits

\*Chi Squared Method, 60% C. L., 55°C & 5.5V; Temperature Derating: Ea = 0.7 ev; Voltage Derating B = 1.0

Temp Cycle  
-55°C to +125°C  
P-20156

<u>300 ~</u>	<u>1K ~</u>	<u>Cum %</u>
--------------	-------------	--------------

Biased Moisture  
85°C/85% RH, 5.5 V.  
P-20157

<u>274 Hr</u>	<u>959 Hr</u>	<u>Cum %</u>
42/0	42/0	0.0%

Autoclave  
121°C/100% RH, 2 Atmos  
P-20158

<u>96 Hr</u>	<u>Cum %</u>
38/0	0.0%

**Failure Mode**

**Failure Analysis**