

**RELIABILITY MONITOR REPORT
FOR**

1.2 μm Process

Dallas Semiconductor

**4401 South Beltwood Parkway
Dallas, TX 75244-3292**

**This Report was prepared by
Dallas Semiconductor Reliability Engineering**

Summary:

The data in the tables that follow was generated as the result of an on-going Process Reliability Monitor. The products covered by this process monitor are:

DS1000	DS1004	DS1012	DS1040	DS1045
DS1202	DS1205	DS1233	DS1267	DS1336
DS1380	DS1384	DS14285	DS1589	DS1602
DS1609	DS1610	DS1620	DS1632	DS1640
DS1648	DS1666	DS1669	DS1688	DS1689
DS1820B	DS1833	DS1867	DS1869	DS2016
DS2107A	DS2130	DS2143	DS2164	DS2165
DS2404	DS2435	DS5001	DS5002	DS50C302
DS9502	DS9503			

The calculated failure rate for devices using this process is:

FAILURE RATE: MTTF (YRS): 18448 FITS: 6.2

The parameters used to calculate this failure rate are as follows:

Cf: 60% Ea: 0.7 B: 0 Tu: 25 °C Vu: 5.5 Volts

The reliability data follows. At the start of this data is the process information. The next section is the detailed reliability data for each stress. The reliability data section includes the latest data available. This report covers data between **and/2006** . 12/31/2006

Device Information:

Process: 1.2 µm Process
Interconnect: Aluminum / 1% Silicon / 0.5% Copper
Gate Oxide Thickness: 225 Å

OPERATING LIFE

DESCRIPTION	DATE CODE	TEST VEHICLE	CONDITION	READPOINT	QUANTITY	FAILS	FA NO
HIGH VOLTAGE LIFE	0549	DS1267	125C, 5.5 V, -4.0V	1000 HRS	80	0	
HIGH TEMP OP LIFE	0614	DS1205	125C, 5.5 VOLTS	1000 HRS	77	0	
Total:						0	

TEMPERATURE CYCLE

DESCRIPTION	DATE CODE	TEST VEHICLE	CONDITION	READPOINT	QUANTITY	FAILS	FA NO
TEMP CYCLE	0549	DS1267	-55C TO 125C	1000 CYS	40	0	
TEMP CYCLE	0614	DS1205	-55C TO 125C	1000 CYS	77	0	
Total:						0	

TEMPERATURE HUMIDITY BIAS

DESCRIPTION	DATE CODE	TEST VEHICLE	CONDITION	READPOINT	QUANTITY	FAILS	FA NO
BIASED MOISTURE	0549	DS1267	85/85, 5.5 VOLTS	1000 HRS	76	0	
BIASED MOISTURE	0614	DS1205	85/85, 5.5 VOLTS	1000 HRS	77	0	
Total:						0	

UNBIASED MOISTURE RESISTANCE

DESCRIPTION	DATE CODE	TEST VEHICLE	CONDITION	READPOINT	QUANTITY	FAILS	FA NO
AUTOCLAVE	0549	DS1267	121C, 2 ATM STEAM, UNBIASED	168 HRS	40	0	
AUTOCLAVE	0614	DS1205	121C, 2 ATM STEAM, UNBIASED	168 HRS	77	0	
				Total:		0	

FAILURE RATE:**MTTF (YRS): 18448****FITS: 6.2**